

Product Data Sheet

SUMITOMO POLYETHYLENE HDPE **B2555**

High Density, Blow Molding

Applications For small to medium sized containers for household and industrial

chemicals, toiletries and cosmetics tubes, automotive supplies, etc.

Characteristics High rigidity, good flowability, and stress crack resistance properties.

Typical Processing Conditions Extrusion temperature: 180°C - 200°C

Mold temperature : 15°C - 40°C

Typical Properties

Physical		Value	Unit	Method
Melt Index	2.16kg	0.25	g/10min	ASTM D1238
	5kg	1.2	g/10min	ASTM D1238
Density		0.954	g/cm ³	ASTM D792-A
Mechanical		Value	Unit	Method
Tensile Strength	_at Yield	27	MPa	ASTM D638
	at Break	34	MPa	ASTM D638
Tensile Elongation	at Break	740	%	ASTM D638
Flexural Modulus		1200	MPa	ASTM D790
Tensile Impact		200	kJ/m²	ASTM D1822
Izod Impact, Notched	23°C	10	kJ/m²	ASTM D256
	-30°C	5	kJ/m²	ASTM D256
Shore Hardness-D		68		ASTM D2240
Thermal		Value	Unit	Method
Vicat Softening Temperature	10N	127	°C	ASTM D1525A
Other		Value	Unit	Method
ESCR, Igepal 10 vol.% solution	F ₅₀	63	h	ASTM D1693

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications, actual test results may vary. Test pieces preparation condition : as per ASTM D4976.



Manufacturer

B2555 is manufactured in Saudi Arabia by Rabigh Refining & Petrochemical Co. (Petro Rabigh). Petro Rabigh is an ISO 9001, ISO 14001, and OHSAS 18001 certified company.

Food Contact Application

Unmodified B2555 complies with the US FDA Regulation 21 CFR 177.1520 as well as the EU Commission Regulation 10/2011, and their respective amendments, for use in direct contact with food. Please contact your nearest SCA representative for more information.

Restriction of Hazardous Substances

The substances regulated under EU Directive 2011/65/EU on RoHS in electrical and electronic equipment are not used in the manufacturing process of B2555 and are therefore not expected to be present.

Storage and Handling

B2555 is supplied in 25kg bags or in bulk containers depending on packaging options available for different markets. It is advisable to store in a well ventilated storage facility, protected from rain, direct exposure to sunlight, temperature, and dust.

Moisture may accumulate inside the packaging if there is a significant fluctuation in ambient temperature and high relative humidity. If this occurs, customer is strongly advised to dry the resin prior to use. Direct exposure to sunlight and excessive ambient temperature may affect the properties, appearance, and odor characteristic of the resin.

Please refer to the Safety Data Sheet (SDS) for information regarding industrial health and safety issues.

Disposal and the Environment

SCA prioritizes environmental management in all our operations in responsibility and respect towards the community and the environment.

Unmodified B2555 is readily recyclable, both for reuse via reprocessing and for energy reclamation through incineration. If disposed in landfills, our products, which are inert materials, do not pose pollution risks since they do not generate gaseous or liquid emissions.

Office Locations

SUMITOMO CHEMICAL ASIA PTE LTD

150 Beach Road, #18-05/08 Gateway West, SINGAPORE 189720

Phone +65 6303 5188 Fax +65 6298 9621 Web Site <u>www.sca.com.sg</u>

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD.

Unit 46-07 Grand Gateway II, No.3 Hongqiao Road, Xu Hui District, Shanghai, CHINA 200030

Phone +86 21 6448 2255 Fax +86 21 6407 7365

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD., GUANGZHOU BRANCH

Room 6404, Office Building, CITIC Plaza, No.233, North Tianhe Road, Guangzhou City, CHINA 510613

Phone +86 20 3877 3577 Fax +86 20 3877 3511

SUMITOMO CHEMICAL ASIA PTE LTD

Vietnam Representative Office, 7th Floor, Unit 701-3, Me Linh Point Tower, 2 Ngo Duc Ke Street, Dist. 01, Ho Chi Minh City, VIETNAM

Phone +84 8 3520 2767 Fax +84 8 3520 2911

SCA SOUTH ASIA PETROCHEMICALS PRIVATE LIMITED

Unit Nos 703 & 704, 7th Floor, Aggarwal Corporate Towers, Plot No 23, District Centre, Rajendra Place, New Delhi 110008, INDIA

Phone +91 11 2575 1572 Fax +91 11 2575 1566

SUMITOMO CHEMICAL EUROPE S.A./N.V.

Woluwelaan, 57, B-1830 Machelen, BELGIUM

Phone +32 2 254 8799 Fax +32 2 251 2991 Web Site <u>www.sumitomo-chem.be</u>

SUMITOMO CHEMICAL EUROPE N.V.

Turkey Liaison Office, Fatih Sultan Mehmet Cad. Yayabeyi Sok. Ilayda Is Mrk, No.12/2, 34810 Kavacik, Beykoz - Istanbul - TURKEY Phone +90 216 680 3334 Fax +90 216 680 1012

Disclaimer

All information contained in this document is provided in good faith and its sole purpose is to provide information regarding SCA's polymer products. This product catalogue is provided on an "as is" basis. SCA makes no representation, warranty, express or implied and assumes no liability as to the accuracy or completeness of any of the information contained in this product catalogue. The values shown are purely values measured on the product and are not to be considered as guaranteed specifications. Any information on this product catalogue should not be considered as a recommendation. Customer is responsible to ensure that SCA materials, whether used alone or mix with other materials, are suitable for the intended application. SCA expressly disclaims for any and all liability, including direct and indirect loss, consequential loss or damages based on or relating to the use or errors of and omissions of such information in this product catalogue. Information contained herein is NOT intended to announce product availability anywhere in the world. Please contact your nearest SCA representative for more detailed information.

Page 2 of 2 Revision 20130121