



ASPC

**Process Optimization**Doc  
Name:

Product Data sheet - LDPE- Low Density Polyethylene

**LTL 2130**

Page: 1 of 2

Doc No.

TEC-PRO-PDS-003

Rev: 5

**Supplier:**Arya Sasol Polymer Company  
Pars special Economic Energy zone**Address:**Tehran office: 7th Floor ,No.2551,  
Kian Tower, (on the corner of Shahid  
Naseri), Valiasr AVE, Tehran- IranPostal code: 1968643111  
P.O.Box: 15875-8393  
Tel: (+9821) 88645201-7 85920000  
Fax: (+9821) 88645209-10

دفتر تهران:

خیابان ولی عصر بالاتر از ظفر نبش کوچه شهید

ناصری- شماره ۲۵۵۱- برج کیان طبقه هفتم

صندوق پستی: ۱۵۸۷۵-۸۳۹۳

کد پستی: ۱۹۶۸۶۴۳۱۱۱

تلفن: ۸۸۶۴۵۲۰۱-۷-۸۵۹۲۰۰۰۰ (+۹۸۲۱)

نمابر: ۸۸۶۴۵۲۰۹-۱۰ (+۹۸۲۱)

**Complex:**Pars Special Economic Energy Zone,  
Assalouyeh-Iran  
Postal code: 75118 – 11365  
P.O.Box : 75118 – 369  
Tel: +98 7727264142- +98 21 85922876-  
78  
Fax: +98 7727264177

مجتمع:

استان بوشهر عسلویه منطقه ویژه اقتصادی پارس

کد پستی: ۷۵۱۱۸ – ۱۱۳۶۵

صندوق پستی: ۷۵۱۱۸ – ۳۶۹

تلفن: ۸۸۲۱۸۵۹۲۲۸۷۶۷۸- +۹۸۷۷۲۷۲۶۴۱۴۲

نمابر: ۷۷۲۷۲۶۴۱۷۷- +۹۸

www. Aryasasol.com

Email: [sop@aspcpe.com](mailto:sop@aspcpe.com)**Typical Data**

Properties	Value	unit	Test method
<b>Physical Properties</b>			
MFI(190 °C /2 .16 Kg )	0.3	Dg/min	ISO 1133
Density	921	Kg/m3	ISO 1183 (A)
<b>Mechanical properties</b>			
Impact strength	31	KJ/m	ASTM D 4272
Tear strength (TD)	45	KN/m	ISO 6383-2
Tear Strength (MD)	20	KN/m	ISO 6383-2
Yield stress (TD)	10	MPa	ISO 527
Yield stress (MD)	11	MPa	ISO 527
Tensile Stress at break (TD)	24	MPa	ISO 527
Tensile Stress at break (MD)	22	MPa	ISO 527
Strain at Break (TD)	>500	%	ISO 527
Strain at Break (MD)	>350	%	ISO 527
Modulus of Elasticity (TD)	150	MPa	ISO 527
Modulus of Elasticity (MD)	140	MPa	ISO 527
<b>Coefficient of friction</b>	0.7		ASTM D 1894
<b>Blocking</b>	<5	g	SABTEC method
<b>Re-blocking</b>	20	g	SABTEC method
<b>Optical properties</b>			
Haze	12	%	ASTM D 1003A
Gloss (45°)	55	%	ASTM D 2457
Clarity	50	mV	SABTEC method
Additive :Antioxidant			

Film properties have been measured at 120µm with a BUR of 3.

**Application**


LTL 2130 can be used for general packaging applications, particularly those requiring a measure of shrink

**General information**

LTL 2130 has been manufactured using SABTEC licensed technology.

**Note:** *this information is based on our current knowledge and experience .in view of many factors that may affect processing and application, this data does not relive processors from the responsibility of carrying out their own tests and experiments, neither does it imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.*

WHEN PRINTED, THIS DOCUMENT IS CONSIDERED TO BE AN UNCONTROLLED DOCUMENT.  
CHECK THE MASTER LIST at <http://sp3/aspc/EDMS/default.aspx> TO VERIFY THAT IS CORRECT VERSION BEFORE USE.

 ASPC	<b>Process Optimization</b>		
	<i>Doc Name:</i>	Product Data sheet - LDPE- Low Density Polyethylene <b>LTL 2130</b>	<i>Page: 2 of 2</i>
	<i>Doc No.</i>	TEC-PRO-PDS-003	<i>Rev: 5</i>

### Processing

LTL2130 is a grade with excellent toughness and outstanding biaxial shrink properties. The material contains only antioxidant, has very low energy consumption during processing and has excellent de\raw down ability

### Packaging

Supplied in pellet form and can be packaged in 25kg bags, 1 ton semi bulk or 17 ton bulk.

### Food packaging

The above mentioned grade meets the relevant requirements of plastics directive 2002/72/EC (06-08-2002) and its amendments till directive 2008/39EC relating to plastic materials and articles intended to come into contact with foodstuffs.

### Pharmaceutical Application

The above mentioned grade meets the requirements of the European pharmacopeia version 6 section 3.1.5 for pharmaceutical application..

### Conveying

Conveying equipment should be designed prevents accumulation of fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

1. be equipped with adequate filters
2. is operated and maintained in such a manner to ensure no leaks develop
3. that adequate grounding exists at all times

We further recommended that good housekeeping will practiced throughout the facility

### Storage

As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight and/or heat during storage. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 OC. It is also advisable to process polyethylene resins (in pelletized or powder from) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality

### Handling

Minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapors.

### Combustibility

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources .in burning; polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

**Note: this information is based on our current knowledge and experience .in view of many factors that may affect processing and application, this data does not relive processors from the responsibility of carrying out their own tests and experiments, neither does it imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.**

**WHEN PRINTED, THIS DOCUMENT IS CONSIDERED TO BE AN UNCONTROLLED DOCUMENT.  
CHECK THE MASTER LIST at <http://sp3/aspc/EDMS/default.aspx> TO VERIFY THAT IS CORRECT VERSION BEFORE USE.**