

Technical Data Sheet
IPETHENE® 810
Low Density Polyethylene



Product Description

IPETHENE® 810 is a low-density polyethylene injection molding grade, produced by high-pressure autoclave technology.

Features:	<ul style="list-style-type: none">No additivesHigh flow	<ul style="list-style-type: none">Low warpage
Uses:	<ul style="list-style-type: none">Caps and closuresHousehold articlesContainers	<ul style="list-style-type: none">BasketsToysMaster-batches
Processing Methods:	<ul style="list-style-type: none">Compounding	<ul style="list-style-type: none">Injection molding

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(190°C/2.16 kg)	ISO 1133	20	g/10 min
Density		ISO 1183-A	0.918	g/cm ³
Shore Hardness	'D' Scale	ISO 868	45	
Thermal				
Peak Melting Temperature	By DSC	ISO 11357-3	108	°C
Vicat Softening Temperature	(10 N)	ISO 306	87	°C
Mechanical				
Tensile Stress at Break		ISO 527-2	9	MPa
Tensile Strain at Break		ISO 527-2	130	%

*Typical values; not to be construed as specifications.

Processing Recommendations

IPETHENE® 810 can be easily processed on conventional injection molding machines. Due to differences in machine type, part shape and mold design, processing conditions should be optimized for each production line. Typical temperature profile: Barrel 160-220°C; Mold 10-40°C.

Health, Quality, Regulations and Safety

This product is not classified as dangerous substance. Material safety data sheets, international standards certificates (e.g. ISO 9001) and other regulatory documents are available on our website. This product is not intended for use in medical or pharmaceutical applications and we do not support its use for such applications.

Carmel Olefins Ltd. POB 1468 Haifa 31014 Israel
Website: <http://www.Carmel-Olefins.co.il>
Email: techserv@caol.co.il

Date: June 2017

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Carmel Olefins extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products.