

# ExxonMobil™ LLDPE LL 1001BU

## Linear Low Density Polyethylene Resin

### Product Description

LL 1001BU offers excellent drawdown and puncture resistance combined with high gloss and clarity. It is frequently used as a blend partner with LDPE resins to improve film properties and processability. TnPP is not intentionally added to LL 1001BU.

### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>Africa &amp; Middle East</li> <li>Asia Pacific</li> </ul>
Additive	<ul style="list-style-type: none"> <li>LL 1001BU: Antiblock: 3500 ppm; Slip: 1500 ppm; Processing Aid: No; Thermal Stabilizer: Yes</li> </ul>
Applications	<ul style="list-style-type: none"> <li>Agricultural Film</li> <li>Bag in Box</li> <li>Barrier Food Packaging</li> <li>Blown Film</li> <li>Bread Bags</li> <li>Food packaging</li> <li>Form Fill And Seal Packaging</li> <li>Freezer Film</li> <li>Garment Film</li> <li>General Packaging</li> <li>Heavy Duty Bags</li> <li>Ice Bags</li> <li>Industrial Liners</li> <li>Industrial Packaging</li> <li>Lamination Film</li> <li>Liners</li> <li>Multilayer Packaging Film</li> <li>Packaging Films</li> <li>Produce Bags</li> <li>Refuse Bags</li> <li>Shoppers</li> <li>Stand Up Pouches</li> <li>Trash Bags</li> </ul>
Revision Date	<ul style="list-style-type: none"> <li>05/22/2018</li> </ul>

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.918 g/cm <sup>3</sup>	0.918 g/cm <sup>3</sup>	ASTM D1505
Melt Index (190°C/2.16 kg)	1.0 g/10 min	1.0 g/10 min	ASTM D1238
Peak Melting Temperature	248 °F	120 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	8700 psi	60 MPa	ASTM D882
Tensile Strength at Break TD	5200 psi	36 MPa	ASTM D882
Elongation at Break MD	570 %	570 %	ASTM D882
Elongation at Break TD	840 %	840 %	ASTM D882
Secant Modulus MD - 1% Secant	29000 psi	200 MPa	ASTM D882
Secant Modulus TD - 1% Secant	32000 psi	220 MPa	ASTM D882
Dart Drop Impact	90 g	90 g	ASTM D1709A
Elmendorf Tear Strength MD	80 g	80 g	ASTM D1922
Elmendorf Tear Strength TD	430 g	430 g	ASTM D1922

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	48	48	ASTM D2457
Haze	13 %	13 %	ASTM D1003

### Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Tris(nonylphenol)phosphite (TNPP) CAS# 26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

### Processing Statement

The film properties have been measured on 30 µm (1.18 mil) thick films. (Blow-up ratio : 2.5)