



## **TECHNICAL DATA SHEET**

**P5300** 

**P5300** is a pipe grade HDPE, produced by the Mitsui CX Process

This resin is recommended for PE 112 pressure pipe applications

**P5300** combines exceptional processability with high creep resistance, high ESCR and excellent mechanical properties

P5300 has a MRS 11.2 MPa according to ISO 9080 and is designated PE 112 according to ISO 12162:1995

Property	Test Method	Unit	Value
Melt Flow Index (5 kg, 190 ℃)	ASTM D1238	g/10 min	0.25
Density (27℃)	ASTM D1505	g/cm <sup>3</sup>	0.948
Physical Property			
Tensile Strength at Yield		MPa	26
Elongation at Yield	ASTM D638	%	8
Tensile Strength at Break	(50 mm/min)	MPa	41
Elongation at Break		%	650
Notched Izod Impact Strength (23 °C)	ASTM D256A	J/m	270
Flexural Modulus	ASTM D790A	MPa	1000
Hardness	ASTM D2240	Shore D	65
ESCR (F <sub>50</sub> , 10% Igepal soln. v/v)	ASTM D1693B	Hr	> 1000
Vicat Softening Point (10 N)	ASTM D1525	°C	125
DSC Melting Temperature	ASTM D3418	°C	131
Oxidative Induction Time	ASTM D3895	Min	> 30
Critical Pressure for Crack Propagation at 0°C	ISO 13477	Bar	≥12
Suggested Processing Conditions			
Barrel Temperature		°C	160 - 220
Die Temperature		C	180 - 220

\* Halene H is the registered trademark of High Density Polyethylene of HPL

Mechanical Properties are on specimens from Compression Molded sheets

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance Certificates & MSDS are available on request. Visit us at www.haldiapetrochemicals.com