

Linear Low Density Polyethylene
Film Extrusion Grade

Melt Index 1.0 Density 0.918

Applications

The *Petrothene* GA501 series of resins is pelletized linear low density polyethylene for film extrusion applications that require excellent drawdown and toughness. These resins have excellent puncture resistance, elongation and heat seal strength. Applications include heavy duty shipping sacks, prime liners, commercial and industrial packaging, as well as food and consumer packaging.

Regulatory Status

The GA501 series resins meet the requirements of the Food and Drug Administration, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components or articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information. GA501 is available without additives or fully formulated with slip and antiblock additives.

Processing Techniques

Typical extrusion conditions are 400°-450°F melt temperature and a 1.5-3.0:1 blow-up ratio. Using proper techniques, these products can readily be drawn below 0.90 mils at optimum production rates. Specific recommendations for type of resin and extrusion conditions can be made only when the end use, required properties and processing equipment are known. For further suggestions, please contact your Equistar sales representative.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index (190/2.16)	1.0	g/10 min	D 1238
Density	0.918	g/cc	D 1505
Vicat Softening Point	107	°C	D 1525
Film			
Gauge	1.0	mil	
Blow-up Ratio	2.5:1		
Haze	20	%	D 1003
Gloss, 45°	40		D 523
Dart Drop Impact Strength, F ₅₀	100	g	D 1709/A
Tensile Strength @ Break, MD (TD)	6,600 (4,700)	psi	D 882
Elongation @ Break, MD (TD)	580 (725)	%	D 882
1% Secant Modulus, MD (TD)	27,000 (28,000)	psi	D 638
Elmendorf Tear, MD (TD)	125 (330)	g	D 1922

Product	<u>GA501020</u>	<u>GA501021</u>	<u>GA501022</u>	<u>GA501023</u>	<u>GA501152</u>
Slip	0	0	1,350	900	600
Antiblock	0	7,000	7,000	5,500	10,000

LyondellBasell markets this product through the following entities:

Equistar Chemicals, LP
Basell Sales & Marketing Company B.V.
Basell Asia Pacific Limited
Basell International Trading FZE
LyondellBasell Australia Pty Ltd

Petrothene is a trademark owned or used by LyondellBasell group companies. *Petrothene* is registered in the U.S. Patent and Trademark Office.

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING.

A LyondellBasell product may not be used in any of the following without prior written approval by LyondellBasell for each specific product and application: U.S. FDA Class II Medical Devices; Health Canada Class II or Class III Medical Devices; European Union Class II Medical Devices; film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned medical devices; packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous administration, and nasal spray or ophthalmic (eye) administration. Further, a LyondellBasell product may not be used in any of the following applications: U.S. FDA Class III Medical Devices; Health Canada Class IV Medical Devices; European Class III Medical Devices; applications involving permanent implantation into the body; and life-sustaining medical applications.

Users should review the applicable Material Safety Data Sheet before handling the product.

Equistar Chemicals, LP
1221 McKinney, Suite 700
P. O. Box 2583
Houston, Texas 77252-2583
(888) 777-0232
www.lyondellbasell.com