



Moplen EP548U

Polypropylene, Impact Copolymer

Product Description

Moplen EP548U is a nucleated heterophasic copolymer with antistatic additivition, suitable for injection moulding applications.

It exhibits an outstanding balance of mechanical properties combined with a very high fluidity.

Moplen EP548U is extensively used in housewares and in thin-walled containers for food packaging (e.g. margerine tubs, yoghurt pots, etc.).

Product Characteristics

| | |
|--------------------------------------|---|
| Status | Commercial: Active |
| Test Method used | ISO |
| Availability | Europe, Africa-Middle East |
| Processing Method | Injection Moulding |
| Features | Antistatic, Impact Copolymer, High Flow , Nucleated |
| Typical Customer Applications | Sports, Leisure and Toys, Housewares, Opaque Containers |

| Typical Properties | Method | Value | Unit |
|---|---------------|-------|-------------------|
| Physical | | | |
| Density | ISO 1183 | 0.9 | g/cm ³ |
| Melt flow rate (MFR) (230°C/2.16Kg) | ISO 1133 | 70 | g/10 min |
| Mechanical | | | |
| Tensile Modulus | ISO 527-1, -2 | 1550 | MPa |
| Tensile Stress at Yield | ISO 527-1, -2 | 28 | MPa |
| Tensile Strain at Break | ISO 527-1, -2 | 30 | % |
| Tensile Strain at Yield | ISO 527-1, -2 | 5 | % |
| Impact | | | |
| Charpy notched impact strength | ISO 179 | | |
| (23 °C, Type 1, Edgewise, Notch A) | | 5.0 | kJ/m ² |
| (0 °C, Type 1, Edgewise, Notch A) | | 3.5 | kJ/m ² |
| (-20 °C, Type 1, Edgewise, Notch A) | | 3.0 | kJ/m ² |
| Ductile/Brittle transition temperature | ISO 6603-2 | -53 | °C |
| Hardness | | | |
| Ball indentation hardness (H 358/30) | ISO 2039-1 | 68 | MPa |
| Thermal | | | |
| Heat deflection temperature B (0.45 MPa) Unannealed | ISO 75B-1, -2 | 95 | °C |
| Vicat softening temperature A/50 | ISO 306 | 151 | °C |
| Vicat softening temperature B/50 | ISO 306 | 80 | °C |

Notes

Typical properties; not to be construed as specifications.

© 2003 Basell Service Company B.V.

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.basell.com/>.

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under LyondellBasell's or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of LyondellBasell except in a writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, incidental, punitive or exemplary damages.

CRP, Adflex, Adstif, Adsyl, Akoalit, Akoafloor, Avant, Catalloy, Clyrell, Entegrity, Get in touch with, Hifax, Higran, Histif, Hostacom, Hostalen, LIPP, Lucalen, Luflexen, Lupocomp, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Moplen, Pristene, Purell, Pro-fax, Sholybox, Softell, Spherilene, Spheripol, Spherizone, Stretchene, Toppyl and Valtec are trademarks owned or used by LyondellBasell group companies.

Adflex, Adstif, Adsyl, Clyrell, CRP, Hifax, Hostacom, Hostalen, Lucalen, Luflexen, Lupolen, Lupotech, Moplen and *Pro-fax* are registered in the U.S. Patent and Trademark Office.

Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.

Release Date: 31 Mar 2009