

# PETILEN G03-21T

## Low Density Polyethylene (LDPE)



### Description

PETILEN G03-21T is a low density polyethylene resin produced by high pressure tubular process. Having high average molecular weight, the product is developed for general purpose applications. PETILEN G03-21T contains no additives.

### Applications

Blown film extrusion: shrink film, agriculture, heavy duty bags

Pipe extrusion: various pipes

### Compliance to Regulations

The formulation and production of PETILEN G03-21T conforms to the compositional requirements of the Commission Regulation (EU) No. 10/2011.

Properties	Typical Value (*)	Unit	Test Method
<b>Resin Properties</b>			
Melt Flow Rate (190°C/2.16 kg)	0.30	g/10 min	ASTM D1238
Density, 23°C	0.921	g/cm <sup>3</sup>	ASTM D1505
Melting Point (DSC)	109	°C	ASTM D3418
<b>Film Properties (**)</b>			
Tensile Strength at Yield, MD	12	MPa	ASTM D882
Tensile Strength at Yield, TD	11	MPa	ASTM D882
Tensile Strength at Break, MD	27	MPa	ASTM D882
Tensile Strength at Break, TD	22	MPa	ASTM D882
Elongation at Break, MD	>250	%	ASTM D882
Elongation at Break, TD	>500	%	ASTM D882
Tear Strength, MD	260	cN	ASTM D1922
Tear Strength, TD	370	cN	ASTM D1922
<b>Optical Properties</b>			
Haze	10	%	ASTM D1003
Gloss, 45°	51	GU	ASTM D2457
<b>Thermal Properties</b>			
Vicat Softening Point, 10 N	98	°C	ASTM D1525

(\*) These are typical properties only and are not to be construed as specifications. Customers should confirm results by their own tests.

(\*\* ) Film properties are measured on 50 µm blown film, Blow up ratio (BUR) 3:1, melt temperature ~205°C.

MD: Machine Direction, TD: Transverse Direction.

# **PETILEN G03-21T**

## **Low Density Polyethylene (LDPE)**



### **Recommended Processing Conditions**

Blown film extrusion applications;

Typical zone temperatures: 160 - 220°C

Typical melt temperature: 190 - 210 °C

Typical blow-up ratio (BUR): 2:1 - 3:1

Due to differences in extrusion, processing conditions should be optimized for each extruder design.

### **Health, Safety and Food Contact Regulations**

The detailed information of the PETILEN G03-21T product is given in Material Safety Data Sheet and Food Contact Declaration of the product. Please contact your sales representatives for the food contact application compliance (e.g. EU, FDA) and other regulatory documents.

### **Storage**

The product should be stored in a dry area with an ambient temperature below 50°C. It should be kept away from sunlight, sparks, heat and flame. Inappropriate storage conditions can lead to color changes and the deterioration in physical properties. It is advised to process PE resins within 6 months after delivery.

### **Recycling**

The product is not hazardous or toxic and it is suitable for recycling. If it can't be recycled, the waste material can be disposed at a suitable landfill site, or at an approved waste incineration facility in accordance with applicable local, provincial, state and federal regulations.

### **Medical Applications Policy**

The product mentioned herein is not tested for use in pharmaceutical/medical applications. It is the responsibility of the final product manufacturer to determine that PETKIM product is suitable for intended use.

### **Disclaimer**

© 2016 PETKIM PETROCHEMICAL HOLDING INC. The user may photocopy, distribute and/or forward this document only if unaltered and complete including its headers, footers and other information. You may not publish this document on a website. PETKIM does not guarantee the typical values. The information in this document relates only to the given product when not in combined or compounded with any other materials. The information in this document is based on data reliable on the date compiled. PETKIM may add, remove and/or update information in this document at any time without noticing the users. PETKIM does not guarantee the merchantability, suitability, fitness for particular purpose, accuracy, reliability or completeness of this information or the products specified. The user is solely responsible for any use of the product at any process. PETKIM disclaims liability for any loss, damage or injury directly or indirectly suffered or incurred as a result or related to anyone using or relying on any information in this document.